

**Amendment to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims**

1. (Original) An ungrounded type flexible fabric container with a reduced energy of electrostatic discharge for use in a combustible environment without the need for antistatic coatings comprising: a woven static dissipating fabric configured to form the flexible fabric container having side walls, a top feature and a bottom feature; and said woven static dissipating fabric comprises fabric woven of non-conductive tapes, to which a plurality of antistatic yarn segments are woven into or coated onto the fabric at a spacing of from 3 mm to 100 mm and wherein the antistatic yarn segments comprise yarn segments of conductive and non-conductive staple fibers and wherein the conductive staple fibers are fibers having a conductive constituent on an outer surface of a non-conductive constituent and wherein the conductive constituent is formed into one or more longitudinal stripes.
2. (Original) An ungrounded type flexible fabric container of claim 1 wherein the woven static dissipating fabric further comprises 11 of 900 denier tapes/inch in the warp direction and 9 of 1300 denier tapes/inch in the weft direction; wherein tapes further comprise polypropylene homopolymer with ultraviolet inhibitors.
3. (Currently amended) An ungrounded type flexible fabric container of claim 2 wherein the antistatic yarn segments comprise 50% by weight non-conductive staple fibers and 50% by weight conductive staple fibers ~~conductive staple yarn is woven into the fabric at a spacing from 10mm to 100 mm.~~

4. (Original) An ungrounded type flexible fabric container of claim 2 wherein the conductive staple yarn is woven into the fabric at a spacing from 10mm to 100 mm.
5. (Original) An ungrounded type flexible fabric container of claim 2 wherein the conductive staple yarn is woven into the fabric at a spacing of 25 mm.
6. (Original) An ungrounded type flexible fabric container of claim 2 wherein the static dissipating fabric further comprises a polymeric coating.
7. (Original) An ungrounded type flexible fabric container of claim 6 wherein the polymeric coating comprises 79.5% weight polypropylene homopolymer; 19% weight low density polyethylene polymer and 1.5% weight ultraviolet inhibitors.
8. (Original) An ungrounded type flexible fabric container of claim 7 wherein the conductive staple yarn is woven into the fabric at a spacing of 25 mm.
9. (Original) An ungrounded type flexible fabric container with a reduced energy of electrostatic discharge for use in a combustible environment without the need for antistatic coatings comprising: a woven fabric configured to form the flexible fabric container having side walls, a top feature and a bottom feature; and said woven fabric made from static dissipating fabric comprising fabric woven of non-conductive tapes of polypropylene having a melt flow index of 1-6 g/10 min. and wherein the tapes have a denier from 500 to 4000 and tape width from 0.07 to 0.40 inches, to which a plurality of antistatic yarn segments are woven into or coated onto the fabric at a spacing of from 3 mm to 100 mm and wherein the antistatic yarn segments comprise yarn segments of conductive and non-conductive staple fibers and wherein the conductive staple fibers are fibers having a conductive constituent on an outer surface of a non-conductive constituent and wherein the conductive constituent is formed into one or more longitudinal stripes.

10. (Original) The container of claim 9 wherein the fabric further comprises a coating layer of polypropylene polymers having a melt flow index greater than 10 g/10 min.
11. (Original) An ungrounded type flexible fabric container with a reduced energy of electrostatic discharge for use in a combustible environment comprising: a woven fabric configured to form the flexible fabric container having side walls, a top feature and a bottom feature; and said woven fabric made from static dissipating fabric comprising fabric woven of non-conductive tapes, to which a plurality of antistatic yarn segments are woven into or coated onto the fabric at a spacing of from 3 mm to 100 mm and wherein the antistatic yarn segments comprise yarn segments of conductive and non-conductive staple fibers and wherein the conductive staple fibers comprise a bicomponent conductive staple fiber having 1 or more longitudinal stripes of a carbon loaded conductive constituent on an outer surface of a non-conductive constituent.
12. (Original) An ungrounded type flexible fabric container of claim 11 wherein the woven fabric further comprises 11 of 900 denier tapes/inch in the warp direction and 9 of 1300 denier tapes/inch in the weft direction; wherein tapes further comprise polypropylene homopolymer with ultraviolet inhibitors.
13. (Original) An ungrounded type flexible fabric container of claim 11 wherein the antistatic yarn segments comprise 50% by weight non-conductive staple fibers and 50% by weight conductive staple fibers.
14. (Original) An ungrounded type flexible fabric container of claim 11 wherein the conductive staple yarn is woven into the fabric at a spacing of 25 mm.
15. (Original) An ungrounded type flexible fabric container of claim 11 wherein the static dissipating fabric further comprises a polymeric coating.
16. (Original) An ungrounded type flexible fabric container of claim 15 wherein the

polymeric coating comprises 79.5% weight polypropylene homopolymer; 19% weight low density polyethylene polymer and 1.5% weight ultraviolet inhibitors.

17. (Original) An ungrounded type flexible fabric container of claim 16 wherein the conductive staple yarn is woven into the fabric at a spacing of 25 mm.
18. (Original) An ungrounded type flexible fabric container with a reduced energy of electrostatic discharge for use in a combustible environment without the need for antistatic coatings comprising: a woven fabric configured to form the flexible fabric container having side walls, a top feature and a bottom feature; and said woven fabric made from static dissipating fabric comprising fabric woven of non-conductive tapes of polypropylene having a melt flow index of 1-6 g/10 min. and wherein the tapes have a denier from 500 to 4000 and tape width from 0.07 to 0.40 inches, to which a plurality of antistatic yarn segments are woven into or coated onto the fabric at a spacing of from 3 mm to 100 mm and wherein the antistatic yarn segments comprise yarn segments of conductive and non-conductive staple fibers and wherein the conductive staple fibers comprise a bicomponent conductive staple fiber having 1 or more longitudinal stripes of a carbon loaded conductive constituent on an outer surface of a non-conductive constituent.
19. (Original) The container of claim 18 wherein the fabric further comprises a coating layer of polypropylene polymers having a melt flow index greater than 10 g/10 min.
20. (Original) The container of claim 18 wherein the antistatic yarn segments comprise 50% by weight non-conductive staple fibers and 50% by weight conductive staple fibers.